

Norbide® Hot Pressed Boron Carbide



Technical Data

Product Description

Norbide® Hot Pressed Boron Carbide (B_4C) is one of the hardest materials known and offers excellent chemical and wear resistance for demanding applications such as blast nozzles, monument nozzles and armor components. Components made with Norbide® B_4C offer longer service life which can translate into lower costs, reduced maintenance and less downtime for many applications.

Applications

- Abrasives for polishing and lapping
- Dressing/forming sticks
- Wear resistant components
- Ballistic armor tiles
- pumping, water jet cutters, etc
- Nozzles for grit blasting slurry

Material Characteristics

- Extreme hardness for wear and abrasion resistance
- High elastic modulus
- Non-porous surface won't react with lubricants and other chemicals
- Good electrical resistivity
- Near theoretical density for longer life

Norbide® Hot Pressed B_4C Typical Physical Properties

Property	Units	Value
Composition*		B•C
Density	gm/cm ³	2.50
Hardness (Knoop)**	kg/mm ²	2800
Flexural Strength 4pt @ RT***	MPa	425
Compressive Strength @ RT	MPa	2900
Modulus of Elasticity @ RT	GPa	440
Poisson's Ratio		0.18
Fracture Toughness @ RT Indentation	MPa x m ^{1/2}	3.1
Coefficient of Thermal Expansion	x10 ⁻⁶ mm/mmK	5
Thermal Conductivity @20°C	W/mK	90


*Composition code: B = boron; C = free graphite; B_4C = boron carbide

**Knoop 0.1 kg load


***Test Bar Size: 3 x 4 x 45mm (0.118" x 0.157" x 1.772")

Saint-Gobain Ceramics application engineers can assist you with the design of cost-effective high performance components for your specific need.

The information recommendations, and opinions set forth herein are offered solely for your consideration, inquiry and verification and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license. Norbide® is a registered trademark of Saint-Gobain Ceramics.



Norbide® Hot Pressed Boron Carbide



Norbide® Boron Carbide micrograph

Saint-Gobain Ceramics
 Structural Ceramics
 Hexoloy® Products
 23 Acheson Drive
 Niagara Falls, New York 14303
 Telephone: 716-278-6233
 Fax: 716-278-2373
 E-mail: scd.sales@saint-gobain.com
www.hexoloy.com

©2004 Saint-Gobain Ceramics
 All Rights Reserved
 Form No. B-1050
 11/04