

SAINT-GOBAIN PERFORMANCE CERAMICS & REFRACTORIES

DURASTRIKE® ZTA

ABRASION RESISTANT CERAMIC FOR SEVERE IMPACT WEAR APPLICATIONS

DESIGNED TO PERFORM & OUTLAST

Durastrike® ZTA, Dense Zirconia Toughened Alumina was designed & developed after extensive field trials and R&D collaboration to overcome abrasion challenges in severe impact applications where traditional materials under perform.

BENEFITS



Improve productivity, profitability
& safety



Reduce downtime & maintenance



Cost effective upgrade to
traditional wear materials




SAINT-GOBAIN

DURASTRIKE® ZTA

Durastrike® ZTA is in a special class of ceramics where zirconia impregnation controls the micro crack propagation within the tile under impact, delivering significant resistance to abrasion and fracture. It significantly outperforms traditional dense aluminium oxide ceramics when considering both impact and erosion.

COMMON FAILURES - EXAMPLES OF TRADITIONAL WEAR MATERIALS

Standard ceramic fracture & joint erosion



Temporary metal patches



DURASTRIKE® ZTA - HIGH PERFORMANCE CERAMIC MATERIAL

No fractures or joint erosion



Durastrike® ZTA delivers increased impact wear against traditional ceramics by 3 – 6 times in applications where the impingement angle is $>30^\circ$ with the conveyed material density between 110 - 165 lb/cu ft (1.76 - 2.64 g/cm³).

Property	Durastrike® ZTA
Density, g/cm ³	> 4.17
Hardness, HV	1900
Fracture Toughness, K_{IC}	6.8
Flexural strength of MOR, MPa	450

TYPICAL MARKETS & APPLICATIONS



Mining (all types)



DRI charging



Material transfer points



Slurry pump components



Port facilities



Sinter plant



Piping components

Leverage Our Expertise.

Saint-Gobain Performance Ceramics & Refractories engineers and researchers collaborate with you, our customers, to solve operational challenges with abrasion resistant ceramic lining systems.

For more information:

www.ceramicsrefractories.saint-gobain.com

ceramics.refractories@saint-gobain.com

Follow us on 



The information contained in this document is believed to be accurate and reliable but is provided without guarantee or warranty on the part of Saint-Gobain Performance Ceramics & Refractories. Process parameters and requirements can impact typical values and test methods. Further, nothing present herein should be interpreted as an authorization or inducement to practice any patented invention without an appropriate license. Saint-Gobain Performance Ceramics & Refractories Terms and Conditions apply to all purchases.

Copyright © 2024, Saint-Gobain Performance Ceramics & Refractories. All rights reserved.