


# Thermal Expansion Coefficient of Hexoloy® SA Silicon Carbide



Saint-Gobain Ceramics  
Structural Ceramics



**Saint-Gobain Ceramics**  
Structural Ceramics  
Hexoloy® Products  
23 Acheson Drive  
Niagara Falls, New York 14303  
Telephone: 716-278-6233  
Fax: 716-278-2373  
E-mail: [scd.sales@saint-gobain.com](mailto:scd.sales@saint-gobain.com)  
[www.hexoloy.com](http://www.hexoloy.com)

©2003 Saint-Gobain Ceramics  
All Rights Reserved  
Form No. B-1006-2 10/03  
Printed in USA

The information, recommendations, and opinions set forth herein are offered solely for your consideration, inquiry and verification and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license.  
Hexoloy® is a trademark of Saint-Gobain Ceramics.

